

510137 Tork Premium Multipurpose Cloth 510 Blanc Bob U/Wiper pack



Chiffon non-tissé en matériau léger permettant de nettoyer dans les moindres recoins
Grande douceur et performance à sec comme humide Contact alimentaire

Information produit

Article	510137
int. Nom	Tork Premium Multipurpose Cloth 510 Blanc Bob U/Wiper pack
SAP Nom	TORK PREMIUM 510 BLANC WIPER PAK
Pays d'origine	Suameer
Code douanier	56031190
Plis	1
Longueur:	152 [m]
Formats:	400
Longueur de format:	38[cm]
Largeur:	32 [cm]
Diamètre:	25 [cm]
Grammage	55 [g/m ²]
Type de fibres	Non tissé
Impression	No
Couleur	Blanche

Spécifications du sous-conditionnement

Unités/sous-conditionnement	1
Poids brut	3.028 [kg]
Poids net	2.675 [kg]
Packaging	
EAN	7322540057263

Spécifications du conditionnement

Packaging	Carton
Nombre de sous-conditionnement	1
Longueur	264 [mm]
Largeur	264 [mm]
Hauteur	335 [mm]
Volume	0.02335 [m ³]
Poids brut	3.028 [kg]
Poids net	2.675 [kg]
EAN	7322540057270

Spécifications de la palette

Conditionnements/palette	72
Couches/palette	6
Volume	1.681 [m ³]
Hauteur	2160 [mm]
EAN	7322540195521

Données environnementales

Chemical pulp Polypropene Polyester Chemicals

Chemical pulp

Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities.

There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free).

ECF is based on oxygene, chlorine dioxide and hydrogen peroxide. TCF is based on hydrogen peroxide and ozone.

ECF is used in this product.

Polypropene

Polypropene fibre is produced from polypropene resin. The resin is melted in an extruder and spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length.

Polyester

Polyester fibre is produced from terephthalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length.

Chemicals

Both functional and process chemicals are used. The functional chemical used is wetstrength agent. The wetstrength agent is a polyamide (from polyamidine/epichlorhydrinepolymer) with a very high affinity to the fibre.

Process chemical used is a surfactant.

This product is produced at Suameer mill, The Netherlands, and certified according to ISO 9001:2000, ISO 14001 and EMAS.

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destructed. The product itself is suitable for incineration. Contact local authorities before destruction.